# XBZ

## **FEATURES**

#### Δrm

Durable corrosion resistant, cast aluminum construction.


## **Finish**

Electrostatically applied TGIC Polyester Powder Coat on substrate prepared with 20 PSI power wash at 140°F. Four step media blast and iron phosphate pretreatment for protection and paint adhesion. 400°F bake for maximum hardness and durability.


### PROJECT TYPE:




Patent pending



**XBZ-UP-2-180** EPA = 1.09





SCALE: 1/2"=1'





